

PRESTIGE RIPOLINE

Prestige Enamel is high quality solvent based enamel paint based on synthetic resins. In vivid shades and long-lasting gloss. High covering capacity. Suitable for metals, woods, plastic and walls both indoors and outdoors.

USAGE

Ideal for surfaces of:

- Metal
- Wood
- Cement

FEATURES

- High gloss & coverage
- High yield
- Excellent spreading
- Very good resistance to cleaning operations



TECHNICAL FEATURES

Shade
Viscosity
Density
Gloss 60°
Surface drying
Recoating time

Various shades
1500 - 2000 mPa•s at 23°C
1.10 ± 0,02 gr/cm³
90
3-4 hrs
24 hrs



(*) The exact time depends on the temperature and relative humidity that prevailing during application and drying.

Yield
Dilution

14-16m²/lt per coating
3 % with White spirit



SURFACE PREPARATION

- It is applied on dry, clean surfaces free of materials that prevent adhesion.
- The success of the application depends on the correct preparation of the substrate and the correct application of the material.
- Removal of silicone or oils from the metal surface with a solvent.
- Prime the metal surface in one or two coats with ANTIRUST or IRON GUARD metal primer.
- Prime the wooden surface in one or two coats with VELATURA.

APPLICATION

- When the primer is dry apply the repoline PRESTIGE layers.
- For adjusting the fluidity it can be diluted by adding 3% White spirit.
- The second coat should be applied after the first coat has dried.

TOOLS CLEANING

During the work keep the tools "wet" in the paint container or tub.
Drain the paint thoroughly from the tools back into the can and clean them with White spirit.

STORAGE

One year in a closed container and storage temperatures between 5oC -35oC

RESTRICTIONS

- Do not apply at temperatures below 5oC or above 35oC
- Do not apply when the relative humidity exceeds 80 %.
- Wet surfaces should be allowed to dry thoroughly before application.

VOC CATEGORY

Product Category A/I (SB) 'One-pack performance coatings' of the EU legislation 2004/42/EU.
Maximum limit VOC value of category: 500gr/lt.
Maximum VOC concentration of ready to use product 499 gr/lt.