

# ANTIRUST ANTICORROSIVE METAL PRIMER

Anticorrosive primer for all metal surfaces. It protects against corrosion, giving long lasting resistance to surfaces exposed to adverse weather conditions and oxidizing environments. It has got excellent adhesion, fast recoating and easy application.

## USAGE

Ideal for surfaces of:

- Metal
- Wood

## FEATURES

- High Adhesion
- Great Coverage
- High Anticorrosive Protection
- High Yield
- Easy To Apply
- Chemical & Mechanical Durability

## TECHNICAL FEATURES

Base
Appearance
Shades
Viscosity
Density
Solids etc.
Ideal Temperature
Surface Drying
Recoating Time
Deep Drying
Yield
Dilution

Alkyd  
Viscous Liquid  
White, Black, Gray, Brick Red  
2000 - 2500 mPa•s at 23°C  
1.50 ± 0,02 gr/cm<sup>3</sup>  
73%  
15-25°C  
1 hr  
24 hrs  
24 hrs  
10-12m<sup>2</sup>/lt per coating  
5% with White Spirit



## SURFACE PREPARATION

- It is applied on dry, clean surfaces free of materials that prevent adhesion.
- The success of the application depends on the correct preparation of the substrate and the correct application of the material.
- Removal of silicone or oils from the metal surface with a solvent.

## APPLICATION

- The surface is primed in two layers with ANTIRUST metal primer.
- For adjusting the fluidity it can be diluted by adding 5% White spirit.
- The second coat should be applied after the first coat has dried.

## TOOLS CLEANING

- During the work keep the tools "wet" in the paint container or tub.
- Drain the paint thoroughly from the tools back into the can and clean them with White spirit.

## STORAGE

- In a closed container and storage temperatures between 5°C and 40°C

## RESTRICTIONS

- Do not apply at temperatures below 5°C or above 35°C
- Do not apply when the relative humidity exceeds 80 %.
- Wet surfaces should be allowed to dry thoroughly before application.
- The freshly painted surface should be protected from cold and moisture for at least 24hrs.

## PDO CATEGORY

Product Category A/i (SB) 'One-Pack performance coatings' of the EU legislation 2004/42/EU.  
Maximum limit VOC value of category: 500gr/lt. Maximum VOC concentration of ready to use productQ 499gr/lt.