

# PRESTIGE ACRYLIC 100%

Water soluble coating for exterior building surfaces.  
Gives a smooth matte velvety surface of excellent aesthetic effect.

## USAGE

Ideal for:

- Concrete
- Plasterboard
- Plaster
- Bricks
- Wood

## FEATURES

- Great adhesion
- Great coverage
- Resistant to weather conditions
- High Yield
- Easy to spread



## TECHNICAL FEATURES

Base
Appearance
Shade
Viscosity
Density
pH
Solids etc.
Ideal temperature
Surface drying
Deep drying
Recoating time
Yield
Dilution

Acrylic
Viscous Liquid
White
7500 - 8000 mPa•s at 23°C
1.52 ± 0,02 gr/cm3
8-9
65%
15-25°C
30min
4hrs
3hrs
10-12m <sup>2</sup> /lt per coating
5-10% with water



## SURFACE PREPARATION

- Applies to dry, clean surfaces free of materials that are not contaminated with materials which prevent adhesion.
- The success of the application depends on the correct preparation of the substrate and the correct application of the material.
- Clean the surface from foreign particles, dust and debris.
- The surface is primed in two layers with either a plastic primer or Desmo Seal solvent thinning primer.

## APPLICATION

- When the primer starts to dry, the CEMENT PAINT is applied PRESTIGE ACRYLIC in two coats.
- To adjust the fluidity it can be diluted by adding 5-10% water.
- The second coat should be applied after the first coat has dried.

## TOOLS CLEANING

During the work keep the tools "wet" in the container or in the paint tub. Drain the paint thoroughly from the tools back into the can and clean them with water.

## STORAGE

One year in closed container, at temperatures between 5°C - 40 °C.

## RESTRICTIONS

- Do not apply at temperatures below 5°C or above 35°C
- Do not apply when the air relative humidity is higher than 80%
- Wet surfaces should be allowed to dry thoroughly before application.
- Freshly painted surface should be protected from cold and moisture for at least 24hr.

## PDO CATEGORY

- Product category A/C (SB) 'Exterior walls of mineral substrate' of the European Directive 2004/42/EC.VOC class limit value : 40 gr/lt. Maximum VOC content of the ready-to-use product is 39 gr/lt.