

CEMENT COLOUR BETOCRYL S-100

Siloxane-based concrete paint specially formulated for exterior use in new or old buildings surfaces such as concrete, plaster, brick etc. Excellent adhesion and stunning finish. Gives the surface a velvety texture without cracks and crazing. Ideal for coastal applications.

USES

Ideal for surfaces from:

- Concrete
- Plasterboard
- Mortar
- Brick
- Wood

SPECIAL FEATURES

- High whiteness
- Perfect coverage
- Weather resistance
- High performance
- Easy to spread

TECHNICAL FEATURES

Base
Display
Hue
Viscosity
Density
pH
Solids etc.
Ideal application and drying temperature:
Surface Drying
Deep drying
Repainting time
Efficiency
Dilution

ACRYLIC

Viscous liquid

White

7500 - 8000 mPa·s at 23°C

1.50 0,02 gr/cm³

8-9

67%

15 - 25°C

30 min

4 hr

3 hr

11-13m²/lt per layer

5-10% with water



SURFACE PREPARATION

- It is applied on dry, clean surfaces free of materials that prevent adhesion.
- The success of the application depends on proper preparation of the substrate and correct application.
- The surface is cleaned of foreign particles, dust and debris.
- Prime the surface in 2 coats with either a plastic primer or Desmo Seal solvent thinner.

APPLICATION

- When the primer starts to dry, apply BETOCRYL S-100 CEMENT PRIMER in 2 coats.
- To adjust the fluidity it can be diluted by adding 5-10% water.
- The second coat should be applied after the first coat has dried.

TOOL CLEANING

- During the work keep the tools "wet" in the container or tub with the paint
- Drain the paint thoroughly from the tools back into the can and clean them with water.

STORAGE

- In a closed container and storage temperatures between 5°C and 40°C

RESTRICTIONS

- Do not apply at temperatures below 5 or above 35°C.
- Do not apply when relative humidity is above 80%.
- Wet surfaces should be allowed to dry thoroughly before application.
- The freshly painted surface should be protected from cold and moisture for at least 24 hours.

PROTECTION

- CONTAINS: mixture of: 5-Chloro-2-methyl-4-isothiazoline-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazole-3-one [EC no. 220-239-6] (3:1)
- May cause an allergic reaction.

PDO CATEGORY

- Product category A/C (Y) Coatings for exterior walls mineral substrate of the European Directive 2004/42/EC. VOC class limit value : 40 gr/lt. Maximum VOC content of the ready-to-use product is 39 gr/lt.

DIMITRIOU S.A.
KORYTSAS 9-KALOCHORI
TEL. 2310-752609
FAX. 2310-752674

info@superlux.gr | www.superlux.gr