



## TECHNICAL CHARACTERISTICS

Hue:	Transparent
Viscosity:	200 - 500 mPa·s at 23°C
Density:	0.83 ± 0,02 gr/cm <sup>3</sup>
Surface drying	1-2 hr
Recoating time (*)	3-4hr
Performance:	10-12m <sup>2</sup> /lt per coat
Dilution	5% with nitro thinner

(\*) The exact time depends on the temperature and relative humidity prevailing during application and drying.

## GENERAL CHARACTERISTICS

STONE CRYL 2000 is transparent varnish of stone, acrylic base and high gloss. It protects, waterproofs and significantly improves the surfaces on which it is applied leaving the feeling of wet stone with a perfect glossy finish. It gives great resistance to abrasion and engraving. It does not turn yellow from the effect of sunlight.

## CHARACTERISTICS

- High gloss
- Long-term endurance
- Excellent finish
- High durability
- Easy to spread
- Resistance to solar radiation

## USES

- Ideal for:
- Stone surfaces

## TOOLS CLEANING

While working, keep the tools "wet" in the container or in the paint bucket. Drain off the paint well from tools into the container and clean them with nitro thinner.

## RESTRICTIONS

- Do not apply at temperatures below 5°C or above 35°C
- Do not apply when the air relative humidity is higher than 80%
- Wet surfaces should be allowed to dry thoroughly before application.

## SURFACE PREPARATION

- It is applied on dry, clean surfaces free of materials that prevent adhesion.
- Application's success depends on the proper preparation of the surface and the correct application of the material.

## APPLICATION

- Apply STONE CRYL 2000 in one or two coats.
- The second coat must be applied after the first one has dried.
- To adjust the fluidity, it can be diluted by adding 5% nitro thinner.

## STORAGE

One year in closed container, at temperatures between 5°C - 35 °C.

## VOC CATEGORY

Product Category A/h (SB) 'Binding Primers' of the EU legislation 2004/42/EU. Maximum limit VOC value of category: 750gr/lt. Maximum VOC concentration of ready to use product 749gr/lt.