



2 in 1 Varnish and Wood Protector



TECHNICAL CHARACTERISTICS

Base	Alkyd
Appearance	Thin liquid
Shades:	Transparent
Viscosity (A+B):	100 - 300 mPa·s at 23°C
Density (A+B):	0.95 ± 0,02 gr/cm ³
Gloss 60°	91
Solids	55%
Ideal temperature of application and drying:	15 - 25oC
Surface Drying	3-4hr
Deep Drying	24hr
Recoating (*):	24hr
Performance	12-14m ² /lt per coat
Dilution:	5% with brush solvent

(*) The exact time depends on the temperature and relative humidity prevailing during application and drying.

GENERAL CHARACTERISTICS

2 in 1 Varnish for Wood Protection alkyd-based paint for wooden surfaces indoors and outdoors. It combines the advantages of wood varnish and protective wood. It protects the wood from the growth of microorganisms as well as from weather conditions and solar radiation. Diluted with Brush extender

CHARACTERISTICS

- High gloss
- Long-term endurance
- Excellent finish
- High efficiency
- Easy to spread
- Resistance to solar radiation
- Resistance to the growth of micro organisms

USES

Ideal for:

- Wooden surfaces

TOOLS CLEANING

While working, keep the tools "damp" in the container or in the paint bucket. Drain off the paint well from tools into the container. Drain the paint well from the tools back to the box and clean them with White spirit.

RESTRICTIONS

- Do not apply at temperatures below 5oC or above 35oC.
- Do not apply when the air relative humidity is higher than 80%.
- Wet surfaces should be allowed to dry thoroughly before application.
- The freshly painted surface should be protected from cold and moisture for at least 24hr.

SURFACE PREPARATION

- It is applied to dry, clean surfaces free from materials that prevent adhesion.
- The success of the application depends on the correct preparation of the substrate and the correct application of the material.

APPLICATION

- Apply 2 in 1 VARNISH & WOOD PROTECTOR in one or two coats
- To adjust the fluidity it can be diluted with the addition of a 5% brush thinner.
- The second coat should be applied after the first one dries.

STORAGE

One year in closed container, at temperatures between 5°C - 35 °C.

VOC CATEGORY

Product Category A/e (SB) 'Interior/exterior trim varnishes and woodstains including opaque woodstains' of the EU legislation 2004/42/EU. Maximum limit VOC value of category: 400gr/lt. Maximum VOC concentration of ready to use product 399gr/lt

